

**AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

1.-7. Canceled.

8. (Previously Presented) The optical glass of claim 23, 24, 25 or 26, which has 0 to 5 % of  $Y_2O_3$ .

9.-14. Canceled.

15. (Previously Presented) The optical glass of claim 23, 24, 25 or 26, wherein part of  $La_2O_3$  is replaced with  $Gd_2O_3$  and/or  $Y_2O_3$ .

16. (Previously Presented) The optical glass of claim 23, 24, 25 or 26, wherein part of  $La_2O_3$  is replaced with  $Gd_2O_3$  and/or  $Y_2O_3$  and the content of  $Li_2O$  is 0 to 1 % by weight.

17. (Previously Presented) A glass preform made of the optical glass recited in claim 23, 24, 25 or 26.

18. (Previously Presented) An optical product made of the optical glass recited in claim 23, 24, 25 or 26.

19. (Original) A process for the production of the optical product recited in claim 18, which comprises the steps of melting raw materials for a glass and directly press-molding a molten glass.

20. (Original) The process of claim 19, which further comprises the step of annealing a glass molded material obtained by the press-molding, after the step of directly press-molding a molten glass.

21. (Original) A process for the production of an optical product, which comprises the steps of softening the glass preform recited in claim 17 under heat and press-molding the glass preform softened under heat.

22. (Original) The process of claim 21, which further comprises the step of annealing a glass molded material obtained by the press-molding, after the step of press-molding the glass preform.

23. (Currently Amended) An optical glass having a refractive index  $n_d$  of at least 1.875, an Abbe's number  $v_d$  of at least 39.5 and a glass transition temperature of 700°C or lower and having a composition comprising, by % by weight,

6 - 9 %	SiO <sub>2</sub> ,
9 - 12 %	B <sub>2</sub> O <sub>3</sub> ,
0 - 5 %	GeO <sub>2</sub> ,
0 - 15 %	ZnO,
30 - 60 %	La <sub>2</sub> O <sub>3</sub> ,
0 - 30 %	Gd <sub>2</sub> O <sub>3</sub> ,
0 - 10 %	Y <sub>2</sub> O <sub>3</sub> ,
0 - 5 %	Yb <sub>2</sub> O <sub>3</sub> ,
2 - 8 %	ZrO <sub>2</sub> ,

13 – 19 %                      Ta<sub>2</sub>O<sub>5</sub>,

the total content of SiO<sub>2</sub> + B<sub>2</sub>O<sub>3</sub> + GeO<sub>2</sub> being 16 to 19 %, the total content of B<sub>2</sub>O<sub>3</sub> + ZnO being at least 9 %, the total content of La<sub>2</sub>O<sub>3</sub> + Gd<sub>2</sub>O<sub>3</sub> + Y<sub>2</sub>O<sub>3</sub> + Yb<sub>2</sub>O<sub>3</sub> being 50 to 60 %, the total content of the above components being at least 95 %,

0 – 3 %                      Li<sub>2</sub>O,

the weight ratio of ZnO/(SiO<sub>2</sub> + B<sub>2</sub>O<sub>3</sub>) being more than 0 but not more than 2,

the weight ratio of (La<sub>2</sub>O<sub>3</sub> + Gd<sub>2</sub>O<sub>3</sub> + Y<sub>2</sub>O<sub>3</sub> + Yb<sub>2</sub>O<sub>3</sub>)/(SiO<sub>2</sub> + B<sub>2</sub>O<sub>3</sub>) being from 2

 to 4,

the weight ratio of (ZrO<sub>2</sub> + Ta<sub>2</sub>O<sub>5</sub> + Nb<sub>2</sub>O<sub>3</sub>)/(SiO<sub>2</sub> + B<sub>2</sub>O<sub>3</sub>) being from 1 to 2,

0 – 3 %                      Nb<sub>2</sub>O<sub>5</sub>, and

0 – 1 %                      WO<sub>3</sub>

wherein the optical glass does not contain HfO<sub>2</sub>.

24. (Currently Amended) An optical glass having a refractive index *nd* of at least 1.875, an Abbe's number *vd* of at least 39.5 and a glass transition temperature of 700°C or lower and having a composition comprising, by % by weight,

6 – 9 %                      SiO<sub>2</sub>,

9 – 12 %                      B<sub>2</sub>O<sub>3</sub>,


0 – 5 %                      GeO<sub>2</sub>,

0 – 15 %                      ZnO,

30 – 60 %                      La<sub>2</sub>O<sub>3</sub>,

0 – 30 %                      Gd<sub>2</sub>O<sub>3</sub>,

0 – 10 %	$\text{Y}_2\text{O}_3$ ,
0 – 5 %	$\text{Yb}_2\text{O}_3$ ,
2 – 8 %	$\text{ZrO}_2$ ,
13 – 19 %	$\text{Ta}_2\text{O}_5$ ,

the total content of  $\text{SiO}_2 + \text{B}_2\text{O}_3 + \text{GeO}_2$  being 16 to 19 %, the total content of  $\text{B}_2\text{O}_3 + \text{ZnO}$  being at least 9 %, the total content of  $\text{La}_2\text{O}_3 + \text{Gd}_2\text{O}_3 + \text{Y}_2\text{O}_3 + \text{Yb}_2\text{O}_3$  being 50 to 60 %, the total content of the above components being at least 95 %, 

0 – 3 %	$\text{Li}_2\text{O}$ ,
---------	-------------------------

the weight ratio of  $\text{ZnO}/(\text{SiO}_2 + \text{B}_2\text{O}_3)$  being more than 0 but not more than 2,

the weight ratio of  $(\text{La}_2\text{O}_3 + \text{Gd}_2\text{O}_3 + \text{Y}_2\text{O}_3 + \text{Yb}_2\text{O}_3)/(\text{SiO}_2 + \text{B}_2\text{O}_3)$  being from 2 to 4,

the weight ratio of  $(\text{ZrO}_2 + \text{Ta}_2\text{O}_5 + \text{Nb}_2\text{O}_5)/(\text{SiO}_2 + \text{B}_2\text{O}_3)$  being from 1 to 2, and

0.5 – 1.5 %  $\text{Nb}_2\text{O}_5$

wherein the optical glass does not contain  $\text{HfO}_2$ .

25. (Currently Amended) An optical glass having a refractive index  $n_d$  of at least 1.875, an Abbe's number  $v_d$  of at least 39.5 and a glass transition temperature of 700°C or lower and having a composition comprising, by % by weight,

6 – 9 %	$\text{SiO}_2$ ,
9 – 12 %	$\text{B}_2\text{O}_3$ ,
0 – 5 %	$\text{GeO}_2$ ,
1 – 7 %	$\text{ZnO}$ ,

30 – 60 %  $\text{La}_2\text{O}_3$ ,


0 – 30 %  $\text{Gd}_2\text{O}_3$ ,

0 – 10 %  $\text{Y}_2\text{O}_3$ ,

0 – 5 %  $\text{Yb}_2\text{O}_3$ ,

2 – 8 %  $\text{ZrO}_2$ ,

13 – 19 %  $\text{Ta}_2\text{O}_5$ ,

the total content of  $\text{SiO}_2 + \text{B}_2\text{O}_3 + \text{GeO}_2$  being 16 to 19 %, the total content of  $\text{B}_2\text{O}_3 + \text{ZnO}$  being at least 12 %, the total content of  $\text{La}_2\text{O}_3 + \text{Gd}_2\text{O}_3 + \text{Y}_2\text{O}_3 + \text{Yb}_2\text{O}_3$  being 50 to 60 %, the total content of the above components being at least 95 %, 

0 – 3 %  $\text{Li}_2\text{O}$ ,

0 – 3 %  $\text{Nb}_2\text{O}_5$ , and

0 – 1 %  $\text{WO}_3$

wherein the optical glass does not contain  $\text{HfO}_2$ .

26. (Currently Amended) An optical glass having a refractive index  $n_d$  of at least 1.875, an Abbe's number  $v_d$  of at least 39.5 and a glass transition temperature of 700°C or lower and having a composition comprising, by % by weight,

6 – 9 %  $\text{SiO}_2$ ,

9 – 12 %  $\text{B}_2\text{O}_3$ ,

0 – 5 %  $\text{GeO}_2$ ,

1 – 7 %  $\text{ZnO}$ ,

30 – 60 %  $\text{La}_2\text{O}_3$ ,


0 - 30 %  $\text{Gd}_2\text{O}_3$ ,

0 - 10 %  $\text{Y}_2\text{O}_3$ ,

0 - 5 %  $\text{Yb}_2\text{O}_3$ ,

2 - 8 %  $\text{ZrO}_2$ ,

13 - 19 %  $\text{Ta}_2\text{O}_5$ ,

the total content of  $\text{SiO}_2 + \text{B}_2\text{O}_3 + \text{GeO}_2$  being 16 to 19 %, the total content of  $\text{B}_2\text{O}_3 + \text{ZnO}$  being at least 12 %, the total content of  $\text{La}_2\text{O}_3 + \text{Gd}_2\text{O}_3 + \text{Y}_2\text{O}_3 + \text{Yb}_2\text{O}_3$  being 50 to 60 %, the total content of the above components being at least 95 %, 

0 - 3 %  $\text{Li}_2\text{O}$ , and

0.5 - 1.5 %  $\text{Nb}_2\text{O}_5$

wherein the optical glass does not contain  $\text{HfO}_2$ .

